

WHAT IS CLAIMED IS:

1. A pre-applied outer layer material for automotive interior trim, which comprises having applied in advance to the back surface of an automotive interior trim a hotmelt
5 having (A) an amorphous poly(α -olefin) having a melting viscosity in the range of 500 - 100,000 mPa·s/190°C, (B) a tackifier resin having a softening point determined by the ring and ball method of not lower than 110°C, and (C) a polypropylene wax having a melting point of not lower than
10 120°C as main components thereof and having a weight ratio of (A) to (C) in the range of 100/50 - 100/100.

2. Apre-appliedouterlayermaterialaccordingtoclaim 2, wherein said outer layer material for automotive interior trim is formed solely of a surface layer material and said
15 hotmelt is directly applied in advance to the back surface of said outer layer material.

3. Apre-appliedouterlayermaterialaccordingtoclaim 2, wherein said outer layer material for automotive interior trim is formed of a surface layer material and a polyolefin
20 foam layer joined to the back surface thereof by adhesion or thermal fusion and said hotmelt is applied to the surface of said polyolefin foam layer.

4. Apre-appliedouterlayermaterialaccordingtoclaim 1, wherein the weight ratio of (A) the amorphous
25 poly(α -olefin)/(B) the tackifier resin is in the range of 100/10 - 100/100.

5. Apre-appliedouterlayermaterialaccordingtoclaim 1, wherein the thickness of said hotmelt applied to the outer layer material is in the range of 10 - 500 μ m.

30 6. Apre-appliedouterlayermaterialaccordingtoclaim 4, wherein said hotmelt further contains not more than 0 weight % of a polyolefin based on the weight of said hotmelt.

7. Apre-appliedouterlayermaterial according to claim 3, wherein said outer layer material is formed solely of a thermoplastic sheet or fibrous material or formed by laminating a polyolefin foam thereon.

5 8. A pre-applied outer layer material for automotive interior trim, which comprises having applied in advance to the back surface of an automotive interior trim a hotmelt having (A) an amorphous poly(α -olefin) having a melting viscosity in the range of 500 - 100,000 mPa·s/190°C, (B) a
10 tackifier resin having a softening point determined by the ring and ball method of not lower than 110°C, and (C) a polypropylene wax having a melting point of not lower than 120°C as main components, having a weight ratio of (A) to (C) in the range of 100/50 - 100/100, and having a weight ratio
15 of (A) the amorphous poly(α -olefin)/(B) the tackifier resin in the range of 100/10 - 100/100.

9. Apre-appliedouterlayermaterial according to claim 7, wherein the weight ratio of (A)/(C) is in the range of 100/30 - 100/60 and the weight ratio of (A)/(B) is in the
20 range of 100/50 - 100/80.

10. A pre-applied outer layer material according to claim 8, wherein said automotive interior trim is formed solely of a surface layer material and said hotmelt is directly applied in advance to the back surface of said surface layer material.

25 11. A pre-applied outer layer material according to claim 8, wherein said automotive interior trim is formed of a surface layer material and a polyolefin foam layer joined by adhesion to the back surface thereof and said hotmelt is applied to the surface of said polyolefin foam layer.

30 12. A method for the production of an automotive interior trim, comprising the steps of applying a pre-applied outer layer material set forth in claim 1 to a molded object and

subjecting them to vacuum forming adhesion without heating the molded object.